

CLAIMS

What is claimed is:

5

1. A film comprising:

a biodegradable polymer; and
a water soluble polymer,

wherein the film is breathable and has a water vapor
transmission rate greater than about $500 \text{ g/m}^2/24\text{hrs}$.

10

2. The film of Claim 1, wherein the biodegradable
polymer is an aliphatic polyester.

15

3. The film of Claim 1, wherein the biodegradable
polymer is selected from the group consisting of polycaprolactone,
polybutylene succinate, poly(butylene succinate-adipate),
polylactic acid, terpolymers of terephthalic acid, adipic acid, and
1,4-butanediol, and copolymers and mixtures thereof.

20

4. The film of Claim 1, wherein the water soluble
polymer is selected from the group consisting of polyethylene
oxide, polyethylene glycol, polyvinyl alcohol, and copolymers and
mixtures thereof.

25

5. The film of Claim 1, wherein the water soluble
polymer is polyethylene oxide, polyethylene glycol or a copolymer
thereof.

30

6. The film of Claim 1 having a water vapor
transmission rate greater than about $1000 \text{ g/m}^2/24\text{hrs}$.

7. The film of Claim 1 having a water vapor
transmission rate greater than about $1500 \text{ g/m}^2/24 \text{ hrs}$.

35

8. The film of Claim 1, wherein the film includes
from about 30% to about 95% biodegradable polymer by weight of
the film.

9. The film of Claim 1, wherein the film includes from about 50% to about 75% biodegradable polymer by weight of the film.

10. The film of Claim 1, wherein the film includes from about 5% to about 70% water soluble polymer by weight of the film.

11. The film of Claim 1, wherein the film includes from about 15% to about 50% water soluble polymer by weight of the film.

12. The film of Claim 1 having an elongation at break of greater than about 350%.

13. The film of Claim 1 having an elongation at break of greater than about 450%.

14. The film of Claim 1 having a thickness of from about 0.01 to about 5 mils.

15. The film of Claim 1 having a thickness of from about 0.01 to about 2 mils.

16. The film of Claim 1, wherein the biodegradable polymer is polycaprolactone and the water soluble polymer is polyethylene oxide.

17. ~~The film of Claim 1, wherein the film is a precursor film.~~

18. The film of Claim 1, wherein the film is biodegradable.

19. The film of Claim 18 having a water vapor transmission rate of greater than about 2500 g/m²/24hrs.

20. The film of Claim 18 having a water vapor transmission rate of greater than about 3000 g/m²/24hrs.

sub
B1

21. The film of Claim 18 having a water vapor transmission rate of greater than about 3500 g/m²/24hrs.

5

22. ~~The film of Claim 18 having an elongation at break of greater than about 100%.~~

10

23. The film of Claim 18 having an elongation at break of greater than about 200%.

24. The film of Claim 18, wherein the film includes from about 1% to about 50% water soluble polymer by weight of the film.

15

25. The film of Claim 18, wherein the film includes from about 5% to about 30% water soluble polymer by weight of the film.

20

26. The film of Claim 18, wherein the film includes from about 50% to about 99% biodegradable polymer by weight of the film.

25

27. The film of Claim 18, wherein the film includes from about 70% to about 95% biodegradable polymer by weight of the film.

28. The film of Claim 18 having a thickness of from about 0.01 to about 5 mils.

30

29. The film of Claim 18 having a thickness of from about 0.01 to about 5 mils.

sub
B1

09640754-042301